

ADVANCENE™ EM-5204-UVH

High Density Polyethylene Resin

Overview:

ADVANCENE™ EM-5204-UVH High Density Polyethylene (HDPE) resin is a hexene copolymer with very narrow molecular weight distribution and produced via advanced gas phase PE process and is intended for use in injection molding applications. This resin has been designed to provide excellent processability for molders and to meet the rigorous performance characteristics of applications requiring excellent stackability, environmental stress crack resistance and impact strength.

Applications:

- Injection molded pails.
- Industrial parts.
- Shipping containers.
- Pallets.

Additives:

Thermal and UV Stabilizers are included.

Complies with:

- Europe EU 10/2011 followed by its amended.
- U.S. FDA 21 CFR 177.1520(c)3.1a

Physical Properties	Nominal Value (SI)	Test Method
Density	0.952 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	4.7 g/10min	ASTM D1238, ISO 1133
Environmental Stress-Cracking Resistance (50°C, 100% Igepal, F50)	24 Hours	ASTM D1693 ¹
Mechanical Properties	Typical Value (SI)	Test Method
Tensile Strength at Yield	25.0 MPa	ASTM D638 ¹ , ISO 527
Tensile Strength at Break	25.0 MPa	
Elongation at Yield	9.5 %	
Elongation at Break	1100 %	
Flexural Modulus 1% Secant	1100 MPa	ASTM D790B ¹ , ISO 178
Flexural Modulus 2% Secant	950 MPa	
Tensile Impact strength	84.0 KJ/m ²	ASTM D1822 ^{1,2} , ISO 8256
Durometer Hardness (Shore D)	59.0	ASTM D2240 ¹ , ISO/IEC 17025:1999
Thermal Properties	Nominal Value (SI)	Test Method
Brittleness Temperature	<-76°C	ASTM D746 ¹ , ISO-974 (E)
Deflection Temperature under load 66 psi (0.45 MPa), Unannealed	72 °C	ASTM D648 ¹ , ISO 75
Vicat Softening Temperature	129 °C	ASTM D1525, ISO 306

Processing Conditions

- Screw speed = 15 – 40 rpm.
- Temperature setting from 200°C - 250°C.

Notes:

1 Molded and tested in accordance with ASTM D4976

2 Type S

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Availability:

This product is supplied in 25 kg bags in secured pallets of 60 bags (1.500 MT net). It is also supplied in jumbo bags of 1000 kg capacity.

Storage:

The product should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product. More information on storage can be found on the Safety Information Sheet for this product.

Safety:

The product is not classified as a hazardous mixture.

Dust and fines from the product carry a risk of dust explosion. All equipment should be properly earthed. Inhalation of dust should be avoided as it may cause irritation of the respiratory system. Small amounts of fumes are generated during processing of the product. Proper ventilation is therefore required.

A Safety Information Sheet is available on request. Please contact your ETHYDCO representative for more details on various aspects of safety, recovery and disposal of the product.

Recycling:

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related documents:

Most datasheets and statements are available on ETHYDCO website www.ethydc0-eg.com. If more information is required, please contact an ETHYDCO representative for information.

Disclaimer:

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

ETHYDCO makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy them with the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of ETHYDCO products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third-party materials.

ADVANCENE™ is a trademark of ETHYDCO